

DUNE™ Second Look®

Scored Tegular
fine texture



Items 2711, 2712, 2722



Dune Second Look I with Prelude® 15/16" Exposed Tee grid; Axiom® Classic Trim

Key Selection Attributes

- Geometric scored visuals
- Upgrade look at modest price
- 30-Year Limited System Warranty against visible sag, mold/mildew and bacterial growth
- Durable – Scratch-resistant

Typical Applications

- Specialty shops/stores
- Corridors
- Offices

Face View Photos



Second Look I scoring creates nominal 12" x 12" squares




Second Look II scoring creates nominal 24" x 24" squares

Detail



DUNE Second Look



DUNE Second Look with SUPRAFINE® 9/16" Exposed Tee grid

Color



White (WH)



DUNE™ Second Look®

Scored Tegular
fine texture

Recycled Content: 45-51%

LEED® Credits

LEED for Schools

Energy	Waste Mgmt	Recycled Content	Local Materials	Renewable Materials	Daylight & Views	Acoustics	Low Emitting or CHPS
✓	✓	✓	✓	✓	✓		✓
Location Dependent							

\$\$\$\$

Visual Selection

Performance Selection Dots represent highest level of performance.

Edge Profile	Item No.	Dimensions	UL Classified		Fire Rating	Light Reflect	Sag Resist	Anti-Microbial	VOC Formaldehyde	Durable	Recycle Program	
			Acoustics NRC	CAC								
DUNE Second Look I												
15/16" Angled Tegular	2711	2' x 4' x 3/4"	[Grid Icon]	0.50	35	Class A	0.83	HumiGuard+	BioBlock+	Low	Scratch	Yes
	2711M	600 x 1200 x 19mm										
DUNE Second Look II												
9/16" Angled Tegular	2722	2' x 4' x 3/4"	[Grid Icon]	0.50	35	Class A	0.83			Low		
	2722M	600 x 1200 x 19mm										
15/16" Angled Tegular	2712	2' x 4' x 3/4"	[Grid Icon]	0.50	35	Class A	0.83			Low		
	2712M	600 x 1200 x 19mm										
	2712NF	2' x 4' x 3/4"										

Suspension Systems

9/16"	Standard: Suprafine®
15/16"	Standard: Prelude®

Physical Data

Material
Wet-formed mineral fiber

Surface Finish
Factory-applied latex paint

Fire Performance
ASTM E84 and CAN/ULC S102 surface burning characteristics. Flame Spread Index 25 or less. Smoke Developed Index 50 or less. (UL labeled)

ASTM E1264 Classification
Type III Form 2, Pattern C E K
Fire Class A

Sag Resistance
HumiGuard® Plus – superior resistance to sagging in high humidity conditions up to, but not including, standing water and outdoor applications.

No-Added Formaldehyde
No-added formaldehyde – free of formaldehyde-based resins. Outperform CHPS Section 01350 requirements. (Independent test reports available upon request.)

Low formaldehyde – contributing less than 13.5 ppb in typical conditions per ASHRAE Standard 62, "Ventilation for Acceptable Indoor Air Quality," California Code Title 24, and other building types in CHPS Section 01350.

Anti Mold/Mildew & Bacteria
BioBlock® Plus contains an anti-microbial treatment and provides guaranteed resistance against growth of mold/mildew and Gram-positive and Gram-negative odor/stain-causing bacteria for 30 years.

Insulation Value
R Factor – 1.6 (BTU units)
R Factor – 0.28 (Watts units)

Backloading Recommendation
Contact TechLine for specific information

30-Year Performance Guarantee & Warranty Information
See warranty details at armstrong.com/warranty

Weight; Square Feet/Carton
1.00 lbs/SF; 80 SF/ctn